

Comparable specifications

EN ISO 1071: SC NiFe-2

Description and applications*

* *Illustrative, not-exhaustive list*

Ferro-nickel solid wire for multi-layer and overlay welding on ferritic and austenitic steel.

The weld metal is characterized by high corrosion and heat resistance.

This grade may be mainly used for:

- repair welds on, as well as joining, work pieces of cast iron, including nodular iron;
- welding work pieces of cast iron to steel and some nonferrous base metals;
- welding non-alloy and high-alloy steel, copper and nickel alloys.
- applications such as rebuilding shafts, wheels, critical joints between steel and cast iron, etc.

Recommended for dissimilar welds of ductile cast iron and non / high alloyed steels.

Weldable base materials*

* *Illustrative, not-exhaustive list*

Grey cast iron, malleable, nodular.

All-weld metal mech. properties*

* *For reference only values*

Tensile strength (Rm): > 500 N/mm²

Chemical composition*

* *For reference only values*

C	Mn	Si	P	S	Fe	Ni	Cu	Al
max	1.00	max	max	max	rem.	45.00	max	max
2.00	5.00	4.00	0.03	0.03		60.00	2.50	1.00

Standard packaging data*

Welding process	Product type	Ø mm (inches)	Packing type	Weight kg (lbs)	Length mm (inches)
GMAW **	filler wire	0.80 - 1.20 (0.030 - 0.047)	spools BS300 / D300	15 (33)	n.a.
GTAW **	filler rod	1.60 - 4.00 (1/16 - 5/32)	cardboard boxes / tubes	5 (11)	1000 (39.4)
SMAW **	core wire for electrodes	1.60 - 5.00 (1/16 - 0.197)	wooden boxes	500 - 750 (1100 - 1650)	250 - 450 (10 - 18)

* *Other sizes and packing types are available upon request*

** *GMAW: gas metal arc welding; GTAW: gas tungsten arc welding; SMAW: shielded metal arc welding*

Marking

Each filler rod for GTAW welding is durably marked with an identification traceable to the unique product type. Welding filler materials wound on spools or in coils are durably marked on the coil or spool with an identification traceable to the unique product type.

The outside of each unit package is suitably labelled with at minimum the following data: grade, diameter, heat, lot no., classifications.

Customized labels are available upon request.

Lot classification

All our productions fulfil the **Class S3** requirements acc. to EN ISO 14344.